

FILM  
INSERT  
HERE

Interior Side

### Benefits and selection criteria

- Helps hold shattered glass together should a break occur
- Helps slow down entry through glass
- Pressure-sensitive adhesive has a low visual distortion that provides optical clarity
- Most often used to help hold shattered glass in place in the event of a windstorm or blast
- Also can be used for added protection during human impact, an earthquake or in the event of spontaneous tempered glass breakage
- Provides good reduction of heat and glare with low interior and exterior reflectance
- Shields >99% of UV radiation, helping to reduce fading of valuables, fabrics and furnishings\*\*
- Please see LLumar.com for recommendations and test results for specific glass and frame types

Manufacturer's  
Limited Warranty\*

# FILM INSERT HERE

Exterior Side

## Performance Data

	% Total Solar Transmittance	% Total Solar Reflectance	% Total Solar Absorbance	% Visible Light Transmittance	% Visible Reflectance (exterior)	% Visible Reflectance (interior)	Winter U-value	Shading Coefficient	% Ultraviolet Ray Protection (wavelengths 300-380nm)	Emissivity	Solar Heat Gain Coefficient	% Total Solar Energy Reflected	Light-to-Solar Heat Gain Ratio (LSG)	% Summer Solar Heat Gain Reduction	% Winter Heat Loss Reduction	% Glare Reduction
Clear Glass 1/8" (3mm) single pane	83	8	9	90	8	8	1.03	1.00	29	0.84	0.86	14	1.05	-	-	-
N1040 SR PS8 1/8" (3mm) single pane	38	14	48	39	16	17	1.06	0.61	>99	0.90	0.53	47	0.74	38	-2	57

## Physical Properties

	Film Thickness (inches)	Appearance	Film Structure	Tensile Strength (constructed)	Tensile Strength (average as reported)	Break Strength (peak load)	Break Strength (average load)	Elongation at Break	Peel Strength	Puncture Strength
N1040 SR PS8	0.008	Medium Neutral	Multi	32,473	32,000	269	260	>100%	>2720 (>6)	164

The solar performance data reported for LLumar architectural window films was captured using the National Fenestration Rating Council's (NFRC) standard guidelines for window film solar performance measurement. All safety and performance data has been measured in accordance with ASTM, ASHRAE, AIMCAL and ANSI standards using NFRC methodology with Lawrence Berkeley National Lab's WINDOW Fenestration Analysis Software. Reported values are taken from representative product samples and are subject to normal manufacturing variances. Actual performance will vary based on a number of factors, including glass type and properties.