

FILM
INSERT
HERE

Interior Side

Benefits and selection criteria

- Helps hold shattered glass together should a break occur
- Pressure-sensitive adhesive has a low visual distortion that provides optical clarity
- Moderately reduces heat gain and glare
- Shields >99% of UV radiation, helping to reduce fading of valuables, fabrics and furnishings**
- Designed for use in museums and historic buildings
- Please see LLumar.com for recommendations and test results for specific glass and frame types

Manufacturer's
Limited Warranty*

FILM INSERT HERE

Exterior Side

Performance Data

	% Total Solar Transmittance	% Total Solar Reflectance	% Total Solar Absorbance	% Visible Light Transmittance	% Visible Reflectance (exterior)	% Visible Reflectance (interior)	Winter U-value	Shading Coefficient	% Ultraviolet Ray Protection (wavelengths 300-380nm)	Emissivity	Solar Heat Gain Coefficient	% Total Solar Energy Reflected	Light-to-Solar Heat Gain Ratio (LSG)	% Summer Solar Heat Gain Reduction	% Winter Heat Loss Reduction	% Glare Reduction
Clear Glass 1/8" (3mm) single pane	83	8	9	90	8	8	1.03	1.00	29	0.84	0.86	14	1.05	-	-	-
NUV65 SR PS4 1/8" (3mm) single pane	64	9	27	69	10	9	1.07	0.83	>99	0.90	0.72	28	0.96	16	-3	23

Physical Properties

	Film Thickness (inches)	Appearance	Film Structure	Tensile Strength (constructed)	Tensile Strength (average as reported)	Break Strength (peak load)	Break Strength (average load)	Elongation at Break	Peel Strength	Puncture Strength
NNUV65 SR PS4	0.004	Very Light Neutral	Multi	33,884	32,000	120	119	>100%	>2720 (>6)	78

The solar performance data reported for LLumar architectural window films was captured using the National Fenestration Rating Council's (NFRC) standard guidelines for window film solar performance measurement. All safety and performance data has been measured in accordance with ASTM, ASHRAE, AIMCAL and ANSI standards using NFRC methodology with Lawrence Berkeley National Lab's WINDOW Fenestration Analysis Software. Reported values are taken from representative product samples and are subject to normal manufacturing variances. Actual performance will vary based on a number of factors, including glass type and properties.